Delrin® SC698 Acetal Resin for Healthcare Devices

Delivering Low Friction for Smooth, Precise Actuation and Injection Performance


Delrin® SC698 acetal resin incorporates a lubricity additive and features the lowest coefficient of friction (COF) in the company's expanded portfolio. Low COF—when moving against itself and other materials—helps Delrin® SC698 resin provide smooth, easy actuation for drug delivery devices like inhalers, injectors and pumps. Patients can benefit from reduced effort, increased comfort, dosing accuracy and consistent operation. Designers and manufacturers can depend on Delrin® SC698 for a smooth surface and good colorability.

Delrin® SC698 resin can also help to improve precise positioning of wearable patches and minimize discomfort when inserting pump connectors by enabling the use of smaller springs.

This highly crystalline homopolymer's strength, stiffness and fatigue resistance, combined with its ultra-low COF, deliver excellent wear properties over time and repeated use. Its high impact resistance helps protect against damage from drops.

For device OEMs, the strength, rigidity and dimensional stability of Delrin® SC698 resin can allow the manufacturing of thin-wall, complex and miniaturized designs without sacrificing performance.

Processability – surface aspect



Low friction POM copolymer | Delrin® SC699 | Delrin® SC698



Pictured: Autoinjector with moving internal components

The medical device industry continues to innovate with portable devices that are making home-care and self-administration more convenient for patients. The unique characteristics of Delrin® acetal resin (lubricity, toughness, stability) play a key role in the success of moving internal components for these devices.

What is SC?

The SC designation in Delrin® SC698 stands for Special Control. Delrin SC resin grades experience a high amount of testing, and they offer a great degree of manufacturing control and broad regulatory compliance.

- Manufactured according to Good Manufacturing Practice (GMP)
- Acquired food contact statements
- Testing against selected parts USP Class VI
- Testing against relevant parts ISO 10993
- Sterilization data
- Global availability

Features


- Ultra-low coefficient of friction
- High tensile strength and stiffness
- Excellent creep resistance and dimensional stability
- High fatigue resistance and impact toughness
- Good colorability
- Attractive surface finish compared to other friction-modified grades
- Sterilizable*

*Not suitable for gamma irradiation and E-beam technology


Benefits

- Smooth, precise actuation of high-load devices for easier patient operation
- Excellent wear/friction performance and durability
- Attractive aesthetics that appeal to patients and encourage use
- Expanded freedom to design thin-wall and complex parts
- System cost reduction through high-volume injection molding
- Avoids need for external lubrication of components

Comparison of Delrin® SC698 with low friction POM copolymer



Coefficient of friction against itself



Target applications

- Drug delivery devices
- Patch/connector inserters
- Gear systems
- Wearables

Target customers

- Medical device OEMs
- Device designers
- Injection molders
- Pharmaceutical OEMs

Delrin® SC698 NC010 acetal resin

Properties	Value	Unit	Test method
Mold shrinkage, normal	1.8	%	ISO 294-4, 2577
Tensile modulus	3100	MPa	ISO 527-1/-2
Yield stress	65	MPa	ISO 527-1/-2
Yield strain	11	%	ISO 527-1/-2
Nominal strain at break	20	%	ISO 527-1/-2
Charpy impact strength, 23°C	150	kJ/m²	ISO 179/1eU
Charpy impact strength, -30°C	150	kJ/m²	ISO 179/1eU
Charpy notched impact strength, 23°C	4	kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30°C	4	kJ/m²	ISO 179/1eA
Poisson's ratio	0.37	-	
Melting temperature, 10°C/min	178	°C	ISO 11357-1/-3
Thermal conductivity of melt	0.22	W/(m K)	
Spec. heat capacity of melt	3020	J/(kg K)	

For complete data visit Delrin® Material Data Center at https://delrin.materialdatacenter.com

To learn more, contact your Delrin representative or visit Delrin.com.

The information and recommendations contained herein are offered as a service to our customers but are not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of these materials. The information and recommendations provided herein were believed by Delrin to be accurate at the time of preparation or obtained from sources believed to be generally reliable. However, Delrin makes no warranty concerning their accuracy and Delrin will not be liable for claims resulting from any party's use of or reliance on information or recommendations contained herein regardless of whether it is claimed that the information or recommendations are inaccurate, incomplete or otherwise misleading. **Caution:** For medical applications, discuss with a Delrin customer representative and consult the Delrin® Medical Caution Statement.

Delrin is an industry-leading premium industrial polymer business. Grounded in strong innovation, Delrin is a category creator with a longstanding reputation for quality, reliability, supply and product performance. The iconic Delrin brand, coupled with proprietary technology and deep application expertise make us a leader in the high-end engineering polymer market. Delrin has exciting growth prospects from exposure to automation, actuation, healthcare, mobility and consumer applications.

Copyright 2024 Delrin

Form no. HMC0324